



The crude stainless steel is defined by its improved resistance to aggressive environment.

Characteristics

The stainless steel sheet EN 1.4301 (AISI 304) is coated, on the external face, with a protective film to remove after installation.

On the internal face (insulating side), it is coated with a fixing primer from 5 to 7 microns (*0.2 to 0.3 mil*).

Thickness : 0,60 mm *0.02"* or 0,80 mm *0.03"*

Finishing : smooth, grain «400»

Recommendation

Inside

The 304 stainless steel sheet, is recommended for inside environment until Ai5, (aggressive environment, with intensive cleaning, saturated humidity, and temperatures until 40°C (*313 K*)).

Outside

The stainless steel sheet is not recommended for outside use.